

OSCCAR EXTRA SOFT PUTTY



Characteristics:

Multi-purpose fill putty. It combines the features of lightweight and multifunctional putties. This product is easy to apply and soft to sand. It provides very good adhesion to various substrates, including steel, galvanized steel, aluminium and polyester substrates. Designed for filling both large and small cavities. Perfect modelling in thick and thin layers. Creates a very smooth and pore-free surface after application.

Application:

The surface must be clean, dry, degreased and matted with abrasives. Thoroughly mix putty by weight with 2-3% of BPO hardener. Apply within 4 - 6 minutes at 20°C. Higher temperature can reduce the pot life and accelerates the drying time.

Note: Using too much hardener can lead to topcoat discoloration. It is not recommended to use putty below 15°C. Do not apply over wash primers and one component acrylic products.

Technical data

VOC content: 2004/42/II B(b)(250) < 250 g/l

Shelf life: 12 months

Density: 1,5 – 1,6 g/cm³

Colour: yellow



Cleaning



Hardener addition

Putty	100 g
BPO Hardener	2-3 g



Body filling

4 - 6 min.



Drying time

20 - 30 min.



Hand sanding / dry

P150 - P320



Machine sanding / dry

P150 - P320



Store in cold place